



Black Polyimide Coverlay

Black Polyimide Coverlay is made of BLACK polyimide film coated by modified stage-B acrylic adhesive on one side with protection release film or paper, widely used in protection of FCPB and other relevant fields.

Characters:

- * Excellent dielectric performance, high bondability and good dimension stability
- * Low fluidity and good processability.
- * In BLACK colour with both polish and matte black available
- * Supplied with different sizes

Spec.:

Models AD/PI/AD (AD=adhesive;PI=polyimide film)	Unit	BPIC-10A 25/25/0
Typical Total Thickness	mm	0.05-0.06
Film Thickness	mm	0.025(1 mil)
Adhesive thickness	mm	0.025-0.035
Supply Size and Packing	Standard roll: 50m ² per roll,width:500mm Carton after winded up into log roll and sealed by plastic film bag, Core ID:3"	

Note: Both customization and epoxy counterpart can also be available.

Typical Properties(The follows are just examples not read as guaranteed values)

Items	Unit	Test Method	Typical datas
1. Peel Strength -As normal conditions -After soldering	N/mm--width	IPC-TM-650-2.4.9	1.1 1.1
2. Dimensional Stability	%	IPC-TM-650-2.2.4A	0.10
3. Adhesive Flow max.(overflow)	um	IPC-TM-650-2.3.17.1	<150
4. Volatile Content	%	IPC-TM-650-2.3.37	≤3.0
5. Soldering resistance	288℃/10sec.	IPC-TM-650-2.4.13	Pass
6. Moisture Absorption	%	IPC-TM-650-2.6.2	≤4.0
7. Dielectric strength	KV/mm	ASTM-D-149	≥30
8. Chemical resistance	%	IPC-TM-650-2.3.2	≥80
9. Dielectric constant	MHZ	IPC-TM-650-2.5.5.3	≤4.0
10.Dissipation factor	-----	IPC-TM-650-2.5.5.3	≤0.04

Storage:

The product is packed in reinforced carton and sealed in plastic film bag. Please keep dry and in room temperature. Shelf life is 12 months.

Note: 1.All of above information is based on our best knowledge, not read as guarantees. Right reserved for corrections.
2.Please contact us if customization requirements.

Contact information: Company: WJF Chemicals Co. Ltd. QuZhou (website: <http://www.wjfchemicals.com>)

Address: 601 ZhongXing Plaza No. 123 HeHua ZhongLu QuZhou ZheJiang Province China
Email: info@wjfchemicals.com Tel./Fax: +865703865831 Mob.:+8613059765326